

PRODUCT DATA SHEET

Seton Code™ Duct Markers

- Identify equipment and airflow in your ductwork system
- Seton Code™ Duct Markers are printed on durable vinyl and pressure sensitive adhesive, perfect for indoor or outdoor use



Description: Seton Code™ Duct Markers are made of pressure sensitive vinyl and come complete with detachable arrows that can be applied in any direction.

Use: Seton Code™ Duct Markers make it easy to differentiate between different air systems.

Adhesive Type: Self-adhesive

Compliance: Seton Code™ Duct Markers meet ASME/ANSI A13.1 standards.

Standard Legend Colors: Black and White

Standard Background Colors: Green, Yellow, and Blue

Thickness (PSTC-33): 0.005 in. (0.127mm.)

Gloss: 8 Gardner Units

Standard Sizes/Dimensions:	Size	Total Marker Size	Arrow Size	Character Size
	GG	16" W x 2-1/4" H	2-3/4" H	1-1/2" H
	HH	24" W x 4" H	3-1/2" H	2-1/2" H

Abrasion Resistance: CS-17 Wheels, 1000g. Wts.

Adhesive Properties: Adhesion to steel (PSTC-1)
15 min. dwell (Avg)—60 oz/in. (65 N/100 mn)
Ultimate (72 hrs. dwell) (Avg)—70 oz/in. (77 N/100 mn)
Tack (ASTM-2979) (Avg)—850g (8 N)

(Method 5306 of U.S. Federal Test Method Std. No. 191A): Legend withstands up to 120 cycle

Minimum Application Temperature: 50°F (10°C)

Service Temperature: -40°F to 180°F (-40°C to 82°C)

Date: ___ / ___ / ___ Job: _____

Contractor _____

PRODUCT DATA SHEET

Seton Code Duct Markers™

Average Outdoor Durability: 2 years (Average expected outdoor life of product will depend on user definition of failure, climatic conditions, mounting techniques, and material color).

Chemical Resistance:	Reagent	7 day Immersion	Dip Test	Rub Test
	30% Sulfuric Acid	NE	NE	NE
	10% Sulfuric Acid	NE	NE	NE
	30% HCL	NE	NE	NE
	10% HCL	NE	NE	NE
	50% NaOH	F	NE	NE
	10% NaOH	F	NE	NE
	10% NaCL	NE	NE	NE
	Methyl Ethyl Ketone	F	F	F
	Acetone	F	F	F
	Methanol	F	NE	NE
	1,1,1, Trichloroethane	F	NE	NE
	IPA (Isopropanol)	F	NE	NE
	ASTM #3 Oil	NE	NE	NE
	SAE 20 Oil	NE	NE	NE
	Mineral Spirits	F	NE	NE
	Diesel Fuel	F	NE	NE
	Heptane	F	NE	NE
	Toluene	F	F	F
	Alconox	NE	NE	NE
	Kerosene	NE	NE	NE
	Bleach	NE	NE	NE
	Water	NE	NE	NE

NE: No Effect F: Failed

7 Day Immersion: Immersed in reagent for 7 days.

Dip Test: Five 10 minute dips in reagent with 30 minute recovery.

Rub Test: Rubbed sample for one minute with swab soaked in reagent.

Shelf Life: 1 year when stored at 70°F (21°C) and 40% to 50% R. H.

Date: ___ / ___ / ___ Job: _____

Contractor _____